

Refractory Steel Anchor - 253MA/S30815



Applications:

- Refractory Industry (Temperature up to 1150°C)
- Reinforced & Refractory Castables
- Petrochemical & Oil Industry
- Cement Industry

Chemical Composition (maximum):

C	Si	N	Ce	S	Cr	Ni	Others
0.10	2.0	0.2	0.08	0.03	20.0-22.0	10.0-12.0	Balance

Melting Temperature	: 1420-1480 °C
Application Temperature	: 1100 °C
Tensile Strength	: 580 MPa (N/mm ²)
Density	: 7.98 (g/cm ³)
Microstructure	: Austenite
Magnetism	: Non
Length	: Customized
Equivalent Diameter	: Customized

HengYang Steel Fiber

Tel: +86-734-8413463

Fax: +86-734-8411922

Mob: +86-17711646910

Email: info@hysteelfiber.com

Web: www.hysteelfiber.com