

# Melt Extract Steel Fiber-ME304

**HENG YANG**



## Applications:

- Refractory Industry (Temperature up to 1000°C)
- Reinforced & Refractory Castables
- Petrochemical & Oil Industry
- Metallurgy Industry

## Chemical Composition (maximum):

C	Si	Mn	P	S	Cr	Ni	others
0.3	2.0	2.0	0.045	0.03	18.0-20.0	8.0-10.5	Balance

<b>Melting Temperature</b>	: 1400-1425 °C
<b>Application Temperature</b>	: 870 °C
<b>Yield Strength</b>	: 210 MPa (N/mm <sup>2</sup> )
<b>Tensile Strength</b>	: 512 MPa (N/mm <sup>2</sup> )
<b>Density</b>	: 7.92 (g/cm <sup>3</sup> )
<b>Microstructure</b>	: Austenite
<b>Magnetism</b>	: Non
<b>Length</b>	: Customized 10 - 50 mm
<b>Equivalent Diameter</b>	: Customized 0.2 - 1.0 mm

# Heng Yang Steel Fiber

Tel: +86-734-8413463

Fax: +86-734-8411922

Mob: +86-17711646910

Email: [info@hysteelfiber.com](mailto:info@hysteelfiber.com)

Web: [www.hysteelfiber.com](http://www.hysteelfiber.com)